

VCOBOND ZN-5720**VCOBOND**

CONSTRUCTION CHEMICALS

DESCRIPTION: -

VCOBOND ZN-5720 is a high build top coat based on a high molecular weight epoxy resin and Zinc chrome pigment and forms a two-component primer with a suitable catalyst. By virtue of the epoxy resin, it has excellent resistance to mild acids, bases and other chemicals. It achieves good build up in one single application. It has outstanding anticorrosive properties and has a good abrasion resistance.

PHYSICAL PROPERTIES: -

TECHNICAL DATA	VCOBOND ZN-5720
COLOR	Zn chrome
SOLIDS	60 %
MIXING RATIO BY VOLUME	1:2
POT LIFE	60 MIN.
INITIAL SETTING	3 HRS.
HARD SET	36 HRS
GEL TIME (77 F)	65-80 MIN.

APPLICATION AREAS: -

Substrates: As an anticorrosive blast primer for tank exteriors, structural steelwork, chemical plant pipelines, cranes steel structures etc., Area of Use: Steel and Metal Structures.

SURFACE PREPARATION:-

Clean the surface free from dust oil and moisture remove the loose materials rust from the surface by mechanical grinding. Apply VCOBOND – RC 200 after 24 hrs. Wash with fresh water. Dry the surface ready to apply VCOBOND ZN-5720

DIRECTION FOR USE:-

- **MIXING** – VCOBOND ZN-5720 Part A & Part B are supplied in a predetermined mixing ratio.
- Pour part B into Part A. Ensure that the Part B drains completely from its container.
- Mixing of the components is to be carried out with a suitable mixture at approx 150-200 rpm.
- Ensure that the two components are evenly dispersed; stir until mix is homogenous mix.
- Apply this mixture by roller or brush.
- Finish the mixture within 25 to 30 min.

CLEAN UP:-

Remove as much product from application equipment as possible before washing with solvent. Do not empty into drains or watercourses

PACKING SIZE:-

VCOBOND ZN-5720 PART A – 1lit & 10 lit.
VCOBOND ZN-5720 PART B – 0.5lit & 5 lit.

COVERAGE:-

Covers approximately 5-5.5 square meter per liter depending up on type of application.

STORAGE & SHELF LIFE:-

6 months if sealed packing and if stored in cool dry place in shaded area.

PRECAUTION: -

Prevent contact of solution with the eyes and mouth. Gloves and rubber gloves must be worn when handling. Liquid splashed on the skin must be rinsed off quickly. If the solution is splashed into the eyes, wash it away with liberal quantity of water and obtain immediate medical attention. Use of mask & safety goggles is must. Clean up any spills, painting tools and equipment with solvent.

LEGAL NOTES:-

The information, and, in particular, the recommendations relating to the application and end-use of View Coating products, are given in good faith based on View Coating's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with View Coating's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. View Coating reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.